# **Technical Data Sheet**



# Additin® RC 2540 EP Additive

### Туре

EP additive; low viscosity, light coloured, active sulphur carrier

# **Technical data\***

Composition	dialkylpentasulphide
Appearance	light coloured, low viscosity liquid
Colour (ASTM-D 1500)	typ. 2.5
Sulphur	approx. 40 % weight
Active sulphur (ASTM-D 1662)	approx. 36 % weight
Copper corrosion (ASTM-D 130) 2.5 % weight Additin RC 2540 in a paraffinic base oil, 3 h/100 °C	3b - 4b
Viscosity, 40 °C (ASTM-D 445)	approx. 45 mm <sup>2</sup> /s
Density, 20 °C (ASTM-D 1298)	approx. 1.0 g/l
Flash point, COC (ASTM-D 92)	approx. 150 °C

## Application

- water miscible metalworking fluids

- neat metalworking fluids

The use of Additin RC 2540 is a good alternative to the sulphurization of base oils with elementary sulphur. In addition, Additin RC 2540 shows with increasing temperatures a steadily increasing active sulphur level (up to max. 38 %) resulting in an effective EP activity at only slightly elevated temperatures (50 to 60 °C). Additin RC 2540 can be successfully combined with other sulphur carriers such as Additin RC 2415 in order to increase EP activity.

The antiwear effect is improved by combination of Additin RC 2540 with zinc dithiophosphates, e.g. Additin RC 3038, phosphoric acid partial esters or ashless phosphorus-sulphur additives e.g. RC 3880

#### Solubility

Soluble in mineral oils and synthetic base oils. However, it is necessary to verify the solubility in the base oils used and the compatibility with other additives.

Page 1 of 3 Edition: 01. Apr 99



# **Technical Data Sheet**

Paraffinic base oil, ISO VG 15



#### **Test results**

	base oil, no additives	+ 2 % b. w. RC 2540	+ 5 % b. w. RC 2540	+ 10 % b. w. RC 2540	+ 15 % b. w. RC 2540	
Four-ball test (DIN 51350, part 2) weld load	600 - 700 N	2200 - 2400 N	2400 - 2600 N	2600 - 2800 N	2800 - 3000 N	
Four-ball test (DIN 51350, part 3) 1 h/300 N scar diameter	0.70 mm	0.80 mm	1.00 mm	1.20 mm	1.50 mm	
Four-ball test (ASTM D-2783) weld point LWI			320 kg 53 kg			
Load-carrying test according to Brugger load capacity	< 20 N/mm²	approx. 65 N/mm²	approx. 65 N/mm²	approx. 65 N/mm²	approx. 80 N/mm²	
Falex Pin and Vee ASTM D-2670-88 load value		3500 lbs	4500 lbs			

### Packing unit

200 kg bunghole drums

### **Storage conditions**

Storage temperature: approx. 20 °C; protect from heat and frost! Shelf life: approx. 12 months

#### Handling

Consult material safety data Sheet (MSDS) for additional handling information on Additin RC 2540.

® = registered trade mark \* The analytical data are guide values.



Page 2 of 3 Edition: 01. Apr 99

# **Technical Data Sheet**



Our technical advice - whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and, therefore, entirely your own responsibility. Should, in spite of this, liability be established for any damage, it will be limited to the value of the goods delivered by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.

LANXESS Deutschland GmbH Business Unit Additives Kennedyplatz 1 D-50569 Cologne, Germany E-Mail: lubricant.additives@lanxess.com http://add.lanxess.com

Page 3 of 3 Edition: 01. Apr 99

